

SOUTHERN LUXE

FLOORING COLLECTION

Vintage Series



Product Specs:

PLANK SPECIFICATION	TEST METHOD	SINGLE PLANK 145mm	SINGLE PLANK 190mm	SINGLE PLANK 240mm	SINGLE PLANK 290mm	SINGLE PLANK 350mm	SINGLE PLANK 400mm
Length		1820mm ± 5mm	1820mm, 2130mm, 2450mm ±5mm			2450mm ± 5mm	3000mm ± 5mm
Width	EN 13489	145mm ± 0.2mm	190mm ± 0.2mm	240mm ± 0.2mm	290mm ± 0.2mm	350mm ± 0.2mm	400mm ± 0.2mm
Total thickness		14.2mm, 22mm ± 0.2mm				22mm ± 0.2mm	
Top layer		3.2mm, 6.02mm ± 0.2mm				6.02mm ± 0.2mm	
Squareness	EN 13489	≤0.2% Over the width					
Cup	EN 13489	≤0.2% Over the width					
Spring	EN 13489	≤0.1% Over the length					
Lipping	EN 13489	≤0.2mm					
Moisture Content	EN 13183-1	7% ± 2% (at the time of delivery)					
Adhesive	EN 717-1	JAPAN F☆☆☆☆~EO					
Finishing	BONA	6 Coats of abrasion resistance ≥ 5000 revolutions ASTM D 4060-CS17					
	KLUMPP	7 Coats of abrasion resistance ≥ 6000 revolutions ASTM D 4060-CS17					
	KLUMPP EMO	3 Coats					
Gloss Value	ISO 2813, 60° angle	BONA NATURALE-4% ± 2%, KLUMPP LACQUER-8%, 45% or 65% gloss level ± 5%					
Formaldehyde Emission	EN 717-1	NO ADDED FORMALDEHYDE					