



Guide To Topcoating Over ZRC

PART 1

DO YOU NEED TO TOPCOAT ZRC?

In most cases, the answer is NO. By definition, "Galvanizing" requires two dissimilar metals (most often zinc and steel) in direct electrical contact so that, theoretically, an electrical charge could be passed through each. In the presence of an electrolyte (rain, water, salt), the zinc (being more susceptible to corrosive attack) corrodes in preference to the steel.

When first applied, the ZRC coating is very porous. Its zinc begins to corrode forming a hard, cementous layer of zinc hydroxycarbonate salt, which closes the pores, making a physical barrier to corrosive attack. Once this salt forms, the rate of zinc corrosion decreases until fresh zinc is exposed by scratching or abrading. This newly exposed zinc forms its salt, filling in the damaged area, essentially "self healing" the anti-corrosion properties of the coating.

Topcoating adds a barrier between the zinc and the electrolyte, thereby slowing down the formation of the zinc salt. This can be good and bad. By blocking the salt formation, the topcoat will increase the service life of the zinc by a factor of approximately 3, dependent on the porosity of the topcoat chosen. The bad is that the porous nature of the zinc coating (as described above) is not changed through salt formation, which could allow moisture to bleed down to the metal surface once it has passed through the topcoat, leading to premature failure. This, of course, is very dependent on topcoat porosity.

Usually, the determining factors for topcoating are the environmental service conditions, aesthetics (ZRC is available only in flat or silvery-grey) and the availability of future on-going maintenance.

In severe environments, such as salt water, acidic (pH<6.5), alkalinity (pH>10.5), chemical fume, etc., we recommend topcoating to avoid premature exhaustion of ZRC's zinc and to prolong service life.

In applications where there will be little or no available maintenance, in order to maximize coating life we recommend topcoating. When maintenance is available, it is best to leave ZRC untopcoated so that additional, fresh ZRC can easily be applied later, if desired. A topcoat would make complete removal by mechanical, chemical or sandblasting means necessary before ZRC could be reapplied.



(800) 831-3275

145 Enterprise Dr., Marshfield, MA 02050

Tel: (781) 319-0400

Fax: (781) 319-0404

Web: www.zrcworldwide.com

E-mail: info@zrcworldwide.com

To the best of our knowledge the technical data contained herein is true and accurate at the date of issuance and is subject to change without prior notice. User must contact ZRC WORLDWIDE to verify correctness before specifying or ordering. No guarantee of accuracy is given or implied. We guarantee our products to conform to ZRC WORLDWIDE quality control. We assume no responsibility for coverage, performance, or injuries resulting from use. Liability, if any, is limited to replacement of products. Prices and cost data, if shown, are subject to change without prior notice. NO OTHER WARRANTY OR GUARANTEE OF ANY KIND is made by ZRC WORLDWIDE, EXPRESS OR IMPLIED, STATUTORY, BY OPERATION OF LAW, OR OTHERWISE, INCLUDING MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Guide To Topcoating Over ZRC

PART 2

SO, YOU'VE DECIDED TO TOPCOAT

WHAT TYPE OF TOPCOAT SHOULD YOU USE?

The following are our general recommendations for topcoat selection and application.

1. The customer must determine the compatibility of the proposed topcoat with ZRC, through proper testing, applied and cured in same manner and at the same film thickness as the anticipated application, under the same anticipated environmental conditions as the proposed application;
2. ZRC is to be applied in one coat to a maximum dry film thickness of 1.5 – 2.0 mils. Surface cleaning by sandblast (SSPC-SP6) is highly recommended;
3. Topcoats to be applied at a maximum dry film thickness of 4.5 – 5.0 mils after 24-48 hours ZRC cure time at 25 °C.

It is critical to ensure that the topcoat chosen has been formulated for use in your particular service environment and for use with zinc-rich coatings. In all cases, contact the topcoat manufacturer for environmental and compatibility data and apply the coating strictly in accordance with the manufacturer's printed instructions.

EPOXY/POLYAMIDE: A two-component system - probably our most recommended. It has excellent chemical resistance, flexibility and impact resistance; and is easy to use. We recommend it for indoor projects only because of epoxy's poor UV light stability; i.e. it will fade and dull during prolonged exposure to light.

ALIPHATIC POLYURETHANE: This can be either a one or two-component coating, which is most often recommended for exterior applications. It has great UV light stability, flexibility and chemical resistance, but can be expensive when compared with epoxies or acrylics.

ACRYLIC ENAMEL: Most often used in automotive work and by small OEM's (Original Equipment Manufacturers), acrylics are inexpensive and OK for use with ZRC provided they are 100% acrylic. Some manufacturers add alkyd oils to their acrylics, which will react with the zinc salt formed when ZRC corrodes, causing blistering and peeling. You must contact the acrylic's manufacturer to determine compatibility.

VINYLS: Another family of low-cost coating, frequently used in wet environments such as water tanks and ocean front locations.

POWDER-COATS: Used often in large scale manufacturing environments, powder-coats have been successfully applied over ZRC. To avoid solvent entrapment within the ZRC layer (which could ultimately lead to pin-holing in the topcoat due to solvent outgassing during powder-coat cure) it is important to cure ZRC at the temperature that will be used to cure the powder-coat. After the ZRC is cured, allow it to cool to room temperature before powder-coat application. For detailed information, please contact ZRC's Technical Department.

DO NOT USE ALKYDS OR LACQUERS!!!

Alkyds, as we discussed above, contains a "Tall Oil" which reacts with the salt formed when zinc corrodes and leads to blistering and peeling. Actually, the reaction is called "Saponification", that is, a zinc soap is formed leaving nothing for the topcoat to stick to.

Lacquer paints, such as those used for expensive automobile restoration, have extremely strong solvents which can soften the ZRC binder, making it easy to remove. Please remember that ZRC is 95% pure zinc and has only 5% binder holding it together.