



Accura Xtreme



A durable, ABS-like plastic well-suited for form, fit and function testing, on demand parts and rapid prototyping master parts.

Measurement	Value
Shore Hardness	86D
Tensile Strength	38 - 44 MPa
Tensile Modulus	1,790 - 1,980 MPa
Flexural Strength	52 - 71 MPa
Flexural Modulus	1,520 - 2,070 MPa
Heat Deflection temp	60° C
Elongation Break	14 - 22%

Actual values may vary depending on build conditions. Our technical team can advise via info@ame-3d.co.uk.

